



PCT

WORLD INTELLECTUAL PROPERTY ORGANIZATION  
International Bureau

INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

(51) International Patent Classification <sup>7</sup> : C08F 10/10, 4/643		A1	(11) International Publication Number: <b>WO 00/04061</b>
			(43) International Publication Date: 27 January 2000 (27.01.00)
(21) International Application Number: PCT/CA99/00644 (22) International Filing Date: 16 July 1999 (16.07.99) (30) Priority Data: 60/093,276 17 July 1998 (17.07.98) US (71) Applicant (for all designated States except US): BAYER INC. [CA/CA]; 1265 Vidal Street South, P.O. Box 3001, Samia, Ontario N7T 7M2 (CA). (72) Inventors; and (75) Inventors/Applicants (for US only): BAIRD, Michael, C. [CA/CA]; 60 Watts Crescent, Kingston, Ontario K7M 2P3 (CA). KARAM, Arquimedes, R. [VE/VE]; Ivic, Cen- trode Quimica, Apartado 21827, Caracas 1020-A (VE). PARENT, Michelle, A. [CA/CA]; 288 Olympus Avenue, Kingston, Ontario K7M 4T9 (CA). (74) Agents: NASSIF, Omar, A. et al.; Gowling, Strathy & Henderson, Suite 4900, Commerce Court West, Toronto, Ontario M5L 1J3 (CA).		(81) Designated States: AE, AL, AM, AT, AU, AZ, BA, BB, BG, BR, BY, CA, CH, CN, CU, CZ, DE, DK, EE, ES, FI, GB, GD, GE, GH, GM, HR, HU, ID, IL, IN, IS, JP, KE, KG, KP, KR, KZ, LC, LK, LR, LS, LT, LU, LV, MD, MG, MK, MN, MW, MX, NO, NZ, PL, PT, RO, RU, SD, SE, SG, SI, SK, SL, TJ, TM, TR, TT, UA, UG, US, UZ, VN, YU, ZA, ZW, ARIPO patent (GH, GM, KE, LS, MW, SD, SL, SZ, UG, ZW), Eurasian patent (AM, AZ, BY, KG, KZ, MD, RU, TJ, TM), European patent (AT, BE, CH, CY, DE, DK, ES, FI, FR, GB, GR, IE, IT, LU, MC, NL, PT, SE), OAPI patent (BF, BJ, CF, CG, CI, CM, GA, GN, GW, ML, MR, NE, SN, TD, TG).  Published With international search report.	

(54) Title: PROCESS FOR POLYMERIZING CATIONICALLY POLYMERIZABLE OLEFIN

## (57) Abstract

A process for polymerizing a cationically polymerizable olefin such as a mixture of isoprene and isobutylene to produce butyl rubber. The process is conducted at subatmospheric pressure in the presence of a conventional cationic polymerization catalyst system. The preferred cationic polymerization catalyst system comprises  $\text{Cp}^*\text{TiMe}_3$  and  $\text{B}(\text{C}_6\text{H}_5)_3$ . By conducting the process in this manner at subatmospheric pressure, a polymer having desirable molecular weight properties may be produced at a higher temperature than conventional means thereby lower capital and operating costs of the plant producing the polymer product.

*FOR THE PURPOSES OF INFORMATION ONLY*

Codes used to identify States party to the PCT on the front pages of pamphlets publishing international applications under the PCT.

AL	Albania	ES	Spain	LS	Lesotho	SI	Slovenia
AM	Armenia	FI	Finland	LT	Lithuania	SK	Slovakia
AT	Austria	FR	France	LU	Luxembourg	SN	Senegal
AU	Australia	GA	Gabon	LV	Latvia	SZ	Swaziland
AZ	Azerbaijan	GB	United Kingdom	MC	Monaco	TD	Chad
BA	Bosnia and Herzegovina	GE	Georgia	MD	Republic of Moldova	TG	Togo
BB	Barbados	GH	Ghana	MG	Madagascar	TJ	Tajikistan
BE	Belgium	GN	Guinea	MK	The former Yugoslav Republic of Macedonia	TM	Turkmenistan
BF	Burkina Faso	GR	Greece			TR	Turkey
BG	Bulgaria	HU	Hungary	ML	Mali	TT	Trinidad and Tobago
BJ	Benin	IE	Ireland	MN	Mongolia	UA	Ukraine
BR	Brazil	IL	Israel	MR	Mauritania	UG	Uganda
BY	Belarus	IS	Iceland	MW	Malawi	US	United States of America
CA	Canada	IT	Italy	MX	Mexico	UZ	Uzbekistan
CF	Central African Republic	JP	Japan	NE	Niger	VN	Viet Nam
CG	Congo	KE	Kenya	NL	Netherlands	YU	Yugoslavia
CH	Switzerland	KG	Kyrgyzstan	NO	Norway	ZW	Zimbabwe
CI	Côte d'Ivoire	KP	Democratic People's Republic of Korea	NZ	New Zealand		
CM	Cameroon			PL	Poland		
CN	China	KR	Republic of Korea	PT	Portugal		
CU	Cuba	KZ	Kazakhstan	RO	Romania		
CZ	Czech Republic	LC	Saint Lucia	RU	Russian Federation		
DE	Germany	LI	Liechtenstein	SD	Sudan		
DK	Denmark	LK	Sri Lanka	SE	Sweden		
EE	Estonia	LR	Liberia	SG	Singapore		

PROCESS FOR POLYMERIZING A CATIONICALLY  
POLYMERIZABLE OLEFIN

TECHNICAL FIELD

5           The present invention relates to a process for polymerizing at least one cationically polymerizable olefin.


BACKGROUND ART

Cationic polymerization of olefins is known in the art.

10           Conventional, cationic polymerization is effected using a catalyst system comprising: (i) a Lewis acid, (ii) a tertiary alkyl initiator molecule containing a halogen, ester, ether, acid or alcohol group, and, optionally, (iii) an electron donor molecule such as ethyl acetate. Such catalyst systems have been used for the so-called "living" and "non-living" carbocationic polymerization of  
15   olefins.

Component (ii) of the catalyst system typically is a compound having the formula:

20



25

wherein  $\text{R}^1$ ,  $\text{R}^2$  and  $\text{R}^3$  are a variety of alkyl or aromatic groups or combinations thereof,  $n$  is the number of initiator molecules and  $\text{X}$  is the functional group on which the Lewis acid effects a change to generate a carbocationic initiation site - i.e.,  $\text{X}$  typically is a halogen, ester, ether, acid  
30   or alcohol group depending on the Lewis acid employed. One or two  $\text{X}$  groups per initiator molecule tends to lead to the production of substantially linear

-2-

polymers, whereas three or more X groups per initiator molecule tends to lead to the production of substantially star polymers.

Catalyst systems based on halogens and/or alkyl-containing Lewis acids, such as boron trichloride and titanium tetrachloride, use various combinations of the above components and typically have similar process characteristics. For the so-called "living" polymerization systems, it is conventional for Lewis acid concentrations to exceed the concentration of initiator sites by 16 to 40 times in order to achieve 100 percent conversion in 30 minutes (based upon a degree of polymerization equal to 890) at -75° to -80°C.

Examples of the so-called "living" polymerization systems are taught in United States patents 4,929,683 and United States patent 4,910,321, the contents of each of which are incorporated herein by reference. Specifically, these patents teach the use of Lewis acids in combination with organic acids, organic esters or organic ethers to form cationic polymerization initiators that also create a complex counter anion. Apparently, the complex counter anion does not assist in or cause proton elimination.

In the so-called "non-living" polymerization systems, high molecular weight polyisobutylenes are prepared practically only at low temperatures (-60 to -100°C) and at catalyst concentrations exceeding one catalyst molecule per initiator molecule. In practice, many of these catalyst systems are applicable only in certain narrow temperature regions and concentration profiles.

In recent years, a new class of catalyst systems utilizing compatible non-coordinating anions in combination with cyclopentadienyl transition metal compounds (also referred to in the art as "metallocenes") has been developed.

See, for example, any one of:

published European patent application 0,277,003A;

published European patent application 0,277,004;

United States patent 5,198,401; and

published International patent application WO92/00333.

-3-

These references teach a method by which the metallocenes (biscyclopentadienyl and monocyclopentadienyl transition metal compounds) are protonated by an anionic precursor such that an alkyl/hydride group is abstracted from a transition metal to make it both cationic and charge-balanced  
5 by the non-coordinating anion.

The use of ionizing compounds not containing an active proton is also known. See, for example, any one of:

published European patent application 0.426.637A; and  
10 published European patent application 0.573.403A.

A further method of making ionic catalysts is disclosed in published European patent application 0,520,732A. Ionic catalysts for addition polymerization can also be prepared by oxidation of the metal centers of transition metal  
15 compounds by anionic pre-cursors containing metallic oxidizing groups along with the anion groups - see, for example, published European patent application 0,495,375A.

It is also known in the art to immobilize the cationic polymerization catalyst system on an inert support material. Methods of supporting ionic  
20 catalysts comprising metallocene cations and non-coordinating anions are described in:

published International patent application WO91/09882; and  
published International patent application WO94/03506.

25

Further, United States patent 5,066,741 teaches the preparation of syndiotactic polystyrene or poly(vinyl aromatics) using non-coordinating anions in combination with cyclopentadienyl transition metal derivatives under coordination catalysis conditions. In United States patents 5,196,490 and  
30 4,808,680 there is disclosed a similar procedure using an alumoxane.

-4-

Jordan, in the Journal of the American Chemical Society (1986, 108, 1718-1719) teaches that tetraphenyl boron forms stable complexes with bis(cyclopentadienyl)zirconium dimethyl, unhindered Lewis bases such as 4,4'-dimethylbipyridine and 4-(dimethylamino) pyridine in CH<sub>3</sub>CN. This reference  
5 also teaches that tetraphenyl boron is stable in THF solution.

The polymerization of olefin monomers comprising isobutylene, including mixtures thereof with small amounts of isoprene to produce butyl rubber, present unique challenges. Specifically, as is well known in the art, since the polymerization reaction is highly exothermic, it is necessary to cool  
10 the reaction mixture to approximately -95°C in large scale production facilities. This requirement has remained notwithstanding advances in the art relating to the development of novel reactor designs and/or novel catalyst systems.

Thus, it would be desirable to have a novel approach to polymerization of cationically polymerizable olefins, particularly olefins such as isobutylene  
15 and mixtures thereof with diolefins (e.g., isoprene), which would allow for the polymerization reaction to be conducted under less stringent temperature regimes. It would be particularly useful if the novel approach could be readily adapted to existing production facilities.

## 20 DISCLOSURE OF THE INVENTION

It is an object of the present invention to obviate or mitigate at least one of the above-mentioned disadvantages of the prior art.

It is another object of the present invention to provide a novel process for polymerizing a cationically polymerizable olefin.

25 It is yet another object of the present invention to provide a novel process for polymerizing an olefin monomer comprising isobutylene.

Accordingly, in one of its aspects, the present invention provides a process for polymerizing a cationically polymerizable olefin comprising the step of polymerizing at least one cationically polymerizable olefin at a  
30 subatmospheric pressure in the presence of a cationic polymerization catalyst system.

-5-

In another of its aspects the present invention provides a process for polymerizing an olefin monomer comprising isobutylene, the process comprising the step of polymerizing the olefin monomer at a subatmospheric pressure at a temperature higher than about  $-80^{\circ}\text{C}$  in the presence of a cationic polymerization catalyst system.

Thus, the present inventor has surprisingly and unexpectedly discovered that it is possible to produce useful polymers by polymerizing a cationically polymerizable olefin at a subatmospheric pressure. This discovery is especially surprising and unexpected when applied to the polymerization of an olefin comprising isobutylene, optionally containing a diolefin such as isoprene. Specifically, the present process is applicable to the production of butyl rubber at temperatures higher than is conventional. This particular application of the process can result in significant savings in capital and operating expenses for a butyl rubber production facility.

#### BEST MODE FOR CARRYING OUT THE INVENTION

Thus, the present process is directed to the polymerization of at least one cationically polymerizable monomer. Of course the present process may be used to polymerize a mixture of monomers comprising the cationically polymerizable monomer. The mixture may comprise another cationically polymerizable monomer and/or another polymerizable monomer.

Preferably, the cationically polymerizable olefin is selected from the group comprising an olefin, a styrenic olefin, a heteroatom olefin and mixtures thereof.

Preferably, the olefin comprises a  $\text{C}_2\text{-C}_{30}$  olefin, more preferably a  $\text{C}_2\text{-C}_{20}$  olefin. Non-limiting examples of a useful olefin may be selected from the group comprising ethylene, propylene, butene, pentene, hexene, heptene, octene, nonene, decene, dodecene, dodecyldocecene, 3-methylpentene-1, 3,5,5-trimethylhexene-1, isobutylene, 2-methyl-butene, 2-methyl-pentene, vinyl ether, vinyl carbazole and mixtures thereof.

-6-

Preferably, the styrenic olefin is selected from the group comprising styrene, C<sub>1</sub>-C<sub>60</sub> alkyl substituted styrene and mixtures thereof. Non-limiting examples of useful styrenic olefins may be selected from the group comprising styrene,  $\alpha$ -methyl styrene, p-chlorostyrene, p-methylstyrene and mixtures thereof.

Preferably, the heteroatom olefin is selected from the group comprising alkyl vinyl ethers, alkyl, amines, alkenyl amines and aryl amines. Non-limiting examples of useful heteroatom olefins may be selected from the group comprising methyl vinyl ether, isobutylvinyl ether, butyl vinyl ether, vinyl carbazole and mixtures thereof.

A preferred monomer comprises a mixture of isobutylene and p-methyl styrene.

In a particularly preferred embodiment, polymerization is conducted in the presence of the at least one cationically polymerizable olefin and a diene monomer. The diene monomer may be conjugated or non-conjugated.

Diolefin monomers are well known in the art and the choice thereof for use in the present process is within the purview of a person skilled in the art. The non-conjugated diolefin can be straight chain, branched chain or cyclic hydrocarbon diolefins having from 6 to 15 carbon atoms. Illustrative nonlimiting examples are straight chain acyclic diolefins such as 1,4-hexadiene and 1,6-octadiene, the branched chain acyclic diolefins such as 5-methylhexadiene-1,4, 7-methyl-octadiene-1,6 and 7-methyl-octadiene-1,7; single ring alicyclic diolefins such as 1,4-cyclohexadiene and 1,5-cyclooctadiene, and multi ring alicyclic fused and bridged ring diolefins such as tetrahydroindene, dicyclopentadiene, 5-ethylidene-2-norbornene, 5-vinylidene-2-norbornene and 5-isopropylidene-2-norbornene. The conjugated diolefin is preferably selected from the group comprising 2,3-dimethyl-butadiene-1,3, isoprene, 1,3-butadiene and mixtures thereof.

As mentioned hereinabove, the present process is particularly advantageous in the preparation of butyl rubber polymers. The term "butyl rubber" as used throughout this specification is intended to denote polymers



-7-

prepared by reacting a major portion, e.g., from about 70 to 99.5 parts by weight, usually 85 to 99.5 parts by weight of an isomonoolefin, such as isobutylene, with a minor portion, e.g., about 30 to 0.5 parts by weight, usually 15 to 0.5 parts by weight, of a multiolefin, e.g., a conjugated diolefin, such as isoprene or butadiene, for each 100 weight parts of these monomers reacted. The isoolefin, in general, is a  $C_4$  to  $C_8$  compound, e.g., isobutylene, 2-methyl-1-butene, 3-methyl-1-butene, 2-methyl-2-butene and 4-methyl-1-pentene. The preferred monomer mixture for use in the production of butyl rubber comprises isobutylene and isoprene. Optionally, an additional olefinic termonomer such as styrene,  $\alpha$ -methylstyrene, p-methylstyrene, chlorostyrene, pentadiene and the like may be incorporated in the butyl rubber polymer. See, for example, any one of:

- United States patent 2,631,984;
- United States patent 5,162,445; and
- United States patent 5,886,106.

The present process is conducted at subatmospheric pressure. Preferably, the pressure at which the present process is conducted is less than about 100 kPa, more preferably less than about 90 kPa, even more preferably in the range of from about 0.00001 to about 50 kPa, even more preferably in the range of from about 0.0001 to about 40 kPa, even more preferably in the range of from about 0.0001 to about 30 kPa, most preferably in the range of from about 0.0001 to about 15 kPa.

The present process comprises the use of a cationic polymerization system.


Preferably, the cationic polymerization system comprises a reactive cation and a compatible non-coordinating anion. The reactive cation may be any cation that can react with an olefin to create a carbocationic polymerization site.

-8-

The terms "compatible non-coordinating anion" and "NCA" are used interchangeably throughout this specification and are intended to encompass an anion which either does not coordinate the cation or which is only weakly coordinated to the cation thereby remaining sufficiently labile to be displaced by an olefin monomer. Further, the term "compatible non-coordinating anion" specifically refers to an anion which, when functioning as a stabilizing anion in the cationic polymerization system used in the present process, does not irreversibly transfer an anionic substituent or fragment thereof to the cation thereby forming a neutral byproduct or other neutral compound. Compatible non-coordinating anions are anions which are not degraded to neutrality when the initially formed complex decomposes.

Non-limiting examples of such compatible non-coordinating anions may be selected from the group comprising alkyltris(pentafluorophenyl) boron ( $\text{RB}(\text{pfp})_3^-$ ), tetrafluorophenylboron ( $\text{B}(\text{pfp})_4^-$ ), tetrafluorophenylaluminum, carboranes, halogenated carboranes and the like.

For clarity, the formulae presented below depict the catalyst components in the "ionic" state. Of course, those of skill in the art will readily realize that many of these components are not stable as depicted and are obtained from a neutral stable form. For example, the species:



25

typically does not exist in this state alone. Rather, it is formed by reacting  $\text{Cp}_2\text{ZrMe}_2$  with another compound that will abstract an Me group. This convention of describing the components in "ionic" form is used for descriptive purposes only and should not be construed as limiting in any way.

30

-9-


The following references teach the neutral stable forms, and the synthesis of the cyclopentadienyl transition metal compositions and the NCA:

- published International patent application WO 92/00333;  
5      published European patent application 0,129,368A;  
published European patent application 0,551,277A  
published European patent application 0,520,732A;  
published European patent application 0,277,003A;  
published European patent application 0,277,004A;  
10      published European patent application 0,426,637A;  
published European patent application 0,573,403A;  
published European patent application 0,520,732A;  
published European patent application 0,495,375A.  
United States patent 5,017,714;  
15      United States patent 5,055,438;  
United States patent 5,153,157; and  
United States patent 5,198,401.

For a description of compounds capable of producing the ionic species  
20      in situ see either of published European patent applications 0,500,944A and  
0,570,982A. These references teach in situ processes comprising the reaction  
of alkyl aluminum compounds with dihalosubstituted metallocene compounds  
prior to or with the addition of activating anionic compounds.

The neutral stable forms of the substituted carbocations and synthesis  
25      thereof are described in United States patent 4,910,321, United States patent  
4,929,683 and published European patent application 0,341,012A. In general,  
the neutral stable form of such carbocations is typically represented by the  
formula:

-10-



5

wherein  $\text{R}_1$ ,  $\text{R}_2$ , and  $\text{R}_3$  are a variety of substituted or unsubstituted alkyl or aromatic groups or combinations thereof,  $n$  is the number of initiator molecules and is preferably greater than or equal to 1, even more preferably between 1 and 30, and  $\text{X}$  is the functional group on which the Lewis acid affects a change to bring about the carbocationic initiating site. This group is typically a halogen, ester, ether, alcohol or acid group depending on the Lewis acid employed.

15

For a discussion of stable forms of the substituted silylium and synthesis thereof, see F.A. Cotton, G. Wilkinson, Advanced Inorganic Chemistry, John Wiley and Sons, New York 1980. Likewise for stable forms of the cationic tin, germanium and lead compositions and synthesis thereof, see Dictionary of Organometallic compounds. Chapman and Hall New York 1984.

20

Thus, as stated hereinabove, the preferred cationic polymerization system comprises: (i) a reactive cation, and (ii) a non-coordinating anion.

A preferred class of compatible non-coordinating anions includes chemically stable, non-nucleophilic substituted anionic complexes.

25


With reference to the non-coordinating anion, any metal or metalloid compound may be used that is capable of forming an anionic complex which is resistant to irreversibly transferring a substituent or fragment to the cation to neutralize the cation to produce a neutral molecule. In addition, any metal or metalloid capable of forming a coordination complex which is stable in water may also be used or contained in a composition comprising the anion. Suitable metals include, but are not limited to, boron, phosphorus, silicon and the like.

30

-11-

Compounds containing anions which comprise coordination complexes containing a single metal or metalloid atom are, of course, well known and many, particularly such compounds containing a single boron atom in the anion portion, are available commercially. In light of this, salts containing anions comprising a coordination complex containing a single boron atom are preferred.

Preferably, the non-coordinating anion has the formula:



10

wherein:

M' is a metal or metalloid;

Q<sub>1</sub> to Q<sub>n</sub> are, independently, bridged or unbridged hydride radicals, dialkylamido radicals, alkoxide and aryloxy radicals, hydrocarbyl and substituted-hydrocarbyl radicals, halocarbyl and substituted-halocarbyl radicals and hydrocarbyl and halocarbyl-substituted organometalloid radicals and any one, with the proviso that not more than one of Q<sub>1</sub> to Q<sub>n</sub> may be a halide radical;

m is an integer representing the formal valence charge of M';

n is the total number of ligands Q; and

d is an integer greater than or equal to 1.

As set out above, it is to be understood that the anions herein are, in practice, counter balanced with a positively charged component that is removed before the anion acts with the reactive cation.

Non-limiting examples of a metal useful as M may be selected from the group comprising aluminum, gold and platinum. Non-limiting examples of a metalloid useful as M may be selected from the group comprising boron, phosphorus and silicon.

In a preferred embodiment:

M' is boron;

n=4;

-12-

$Q_1$  and  $Q_2$  are the same or different aromatic or substituted-aromatic hydrocarbon radicals containing from about 6 to about 20 carbon atoms and may be linked to each other through a stable bridging group; and

5  $Q_3$  and  $Q_4$  are, independently, hydride radicals, hydrocarbyl and substituted-hydrocarbyl radicals, halocarbyl and substituted-halocarbyl radicals, hydrocarbyl- and halocarbyl-substituted organometalloid radicals, disubstituted pnictogen radicals, substituted chalcogen radicals and halide radicals, with the proviso that  $Q_3$  and  $Q_4$  will not be halide at the same time.

Non-limiting examples of boron components which may be used as  
10 NCA's may be selected from the group comprising: tetra-valent boron compounds such as tetra(phenyl)boron, tetra(p-tolyl)boron, tetra(o-tolyl)boron, tetra(pentafluorophenyl)boron, tetra(o,p-dimethylphenyl)boron, tetra(m,m-dimethylphenyl)boron, (p-tri-fluoromethylphenyl)boron and mixtures thereof.

In a particularly preferred embodiment,  $M = \text{boron}$ ,  $n = 4$ ,  $Q_1$ ,  $Q_2$  and  
15  $Q_3$  are each ( $C_6F_5$ ) and  $Q_4$  is as defined above. Non-limiting examples of those preferred NCA's comprising boron triphenylmethyl salts where  $Q$  is a simple hydrocarbyl such as methyl, butyl, cyclohexyl, or phenyl or where  $Q$  is a polymerix hydrocarbyl of indefinite chain length such as polystyrene, polyisoprene or poly(paramethylstyrene).

20 Another preferred class of NCA's is the class comprising those NCA comprising a plurality of boron atoms, including boranes and carboranes. Non-limiting examples of carborane NCA's may be selected from the group comprising: dodecaborate, decachlorodecaborate, dodecachlorododecaborate, 1-carbadecaborate, 1-carbaundecaborate, 1-trimethylsilyl-1-carbadecaborate and  
25 mixtures thereof. Non-limiting examples of borane and carborane complexes and salts of borane and carborane anions may be selected from the group comprising decaborane(14), 7,8-dicarbadecaborane(13), 2,7-dicarbaundecaborane(13), undecahydrido-7,8-dimethyl-7,8-dicarbaundecaborane, 6-carbadecaborate(12), 7-carbaundecaborate, 7,8-  
30 dicarbaundecaborate.

-13-

Further, NCA's comprising metallaborane anions are also useful. Non-limiting examples of such NCA's may be selected from the group comprising bis(nonahydrido-1,3-dicarbanonaborato)cobaltate(III), bis(undecahydrido-7,8-dicarbaundecaborato)ferrate(III), bis(undecahydrido-7,8-dicarbaundecaborato)cobaltate(III), bis(undecahydrido-7,8-dicarbaborato) nikelate(III), bis(nonahydrido-7,8-dimethyl-7,8-dicarbaundecaborato)ferrate(III), bis(tribromooctahydrido-7,8-dicarbaundecaborato)cobaltate(III), bis(undecahydridodicarbadodecaborato)cobaltate(III), bis(undecahydrido-7-carbaundecaborato) cobaltate(III) and mixtures thereof.

10 The NCA compositions most preferred for use in the cationic polymerization system are those containing a tris-perfluorophenyl boron, tetrapentafluorophenyl boron anion and/or two or more tripentafluorophenyl boron anion groups covalently bonded to a central atomic molecular or polymeric complex or particle.

15 The other component in the preferred cationic polymerization catalyst system comprises one or more reactive cations that are selected from different classes of cations and cation sources. Some preferred classes are:

(A) cyclopentadienyl transition metal complexes and derivatives thereof;

(B) substituted carbocations;


20 (C) substituted silylium;

(D) compositions capable of generating a proton as further described below; and

(E) cationic compositions of germanium, tin or lead.

25 With reference to class (A), preferred cyclopentadienyl metal derivatives may be selected from the group comprising compounds that are a mono-, bis- or tris-cyclopentadienyl derivative of a transition metal selected from Groups 4, 5 or 6 of the Periodic Table of Elements. Preferred compositions include mono- cyclopentadienyl (Mono-Cp) or bis-cyclopentadienyl (Bis-Cp) Group 4 transition metal compositions, particularly zirconium, titanium and/or hafnium  
30 compositions.

Preferred cyclopentadienyl derivatives are transition metal complexes selected from the group comprising:



wherein:

(A-Cp) is either (Cp)(Cp\*) or Cp-A'-Cp\*:

- 5 Cp and Cp\* are the same or different cyclopentadienyl rings substituted with from 0 to 5 substituent groups S, each substituent group S being, independently, a radical group selected from the group comprising hydrocarbyl, substituted-hydrocarbyl, halocarbyl, substituted-halocarbyl, hydrocarbyl-substituted organometalloid, halocarbyl-substituted organometalloid,
- 10 disubstituted boron, disubstituted pnictogen, substituted chalcogen or halogen radicals, or Cp and Cp\* are cyclopentadienyl rings in which any two adjacent S groups are joined forming a C<sub>4</sub> to C<sub>20</sub> ring system to give a saturated or unsaturated polycyclic cyclopentadienyl ligand;

- R is a substituent on one of the cyclopentadienyl radicals which is also
- 15 bonded to the metal atom;

A' is a bridging group, which group may serve to restrict rotation of the Cp and Cp\* rings or (C<sub>5</sub>H<sub>5-y-x</sub>S<sub>x</sub>) and JR'(<sub>z-1-y</sub>) groups;

M is a Group 4,5, or 6 transition metal;

y is 0 or 1;



-15-

(C<sub>5</sub>H<sub>5-y-x</sub>S<sub>x</sub>) is a cyclopentadienyl ring substituted with from 0 to 5 S radicals;

x is from 0 to 5;

JR'(<sub>z-1-y</sub>) is a heteroatom ligand in which J is a Group 15 element with a coordination number of three or a Group 16 element with a coordination number of 2, preferably nitrogen, phosphorus, oxygen or sulfur;

R" is a hydrocarbyl group;

X and X<sup>1</sup> are independently a hydride radical, hydrocarbyl radical, substituted hydrocarbyl radical, halocarbyl radical, substituted halocarbyl radical, and hydrocarbyl- and halocarbyl-substituted organometalloid radical, substituted pnictogen radical, or substituted chalcogen radicals; and

L is an olefin, diolefin or aryne ligand, or a neutral Lewis base.

Other cyclopentadienyl compounds that may be used in the cationic polymerization catalyst system are described in:

15

published European patent application 0,551,277A:

United States patent 5,055,438;

United States patent 5,278,119;


United States patent 5,198,401; and

20

United States patent 5,096,867.

With reference to class (B), a preferred group of reactive cations comprises carbocationic compounds having the formula:

25




30

wherein R<sup>1</sup>, R<sup>2</sup> and R<sup>3</sup>, are independently hydrogen, or a linear, branched or cyclic aromatic or aliphatic group, with the proviso that only one of R<sup>1</sup>, R<sup>2</sup> and

-16-

$R^3$  may be hydrogen. Preferably, none of  $R^1$ ,  $R^2$  and  $R^3$  are H. Preferably,  $R^1$ ,  $R^2$  and  $R^3$ , are independently a  $C_1$  to  $C_{20}$  aromatic or aliphatic group. Non-limiting examples of suitable aromatic groups may be selected from the group comprising phenyl, tolyl, xylyl and biphenyl. Non-limiting examples of suitable aliphatic groups may be selected from the group comprising methyl, ethyl, propyl, butyl, pentyl, hexyl, octyl, nonyl, decyl, dodecyl, 3-methylpentyl and 3,5,5-trimethylhexyl.

With reference to class (C), a preferred group of reactive cations comprises substituted silylium cationic compounds having the formula:



15


wherein  $R^1$ ,  $R^2$  and  $R^3$ , are independently hydrogen, or a linear, branched or cyclic aromatic or aliphatic group, with the proviso that only one of  $R^1$ ,  $R^2$  and  $R^3$  may be hydrogen. Preferably, none of  $R^1$ ,  $R^2$  and  $R^3$  are H. Preferably,  $R^1$ ,  $R^2$  and  $R^3$  are, independently, a  $C_1$  to  $C_{20}$  aromatic or aliphatic group. More preferably,  $R^1$ ,  $R^2$  and  $R^3$  are independently a  $C_1$  to  $C_6$  alkyl group. Non-limiting examples of useful aromatic groups may be selected from the group comprising phenyl, tolyl, xylyl and biphenyl. Non-limiting examples of useful aliphatic groups may be selected from the group comprising methyl, ethyl, propyl, butyl, pentyl, hexyl, octyl, nonyl, decyl, dodecyl, 3-methylpentyl and 3,5,5-trimethylhexyl. A particularly preferred group of reactive substituted silylium cations may be selected from the group comprising trimethylsilylium, triethylsilylium and benzyldimethylsilylium. Such cations may be prepared by the exchange of the hydride group of the  $R^1R^2R^3Si-H$  with the NCA, such as  $Ph_3C^+B(pfp)_4^-$  yielding compositions such as  $R^1R^2R^3SiB(pfp)_4$  which in the appropriate solvent obtain the cation.

-17-

With reference to class (D), the source for the cation may be any compound that will produce a proton when combined with the non-coordinating anion or a composition containing a non-coordinating anion. Protons may be generated from the reaction of a stable carbocation salt which contains a non-coordinating, non-nucleophilic anion with water, alcohol or phenol to produce the proton and the corresponding by-product. Such reaction may be preferred in the event that the reaction of the carbocation salt is faster with the protonated additive as compared with its reaction with the olefin. Other proton generating reactants include thiols, carboxylic acids, and the like. Similar chemistries may be realized with silylium type catalysts. In another embodiment, when low molecular weight polymer product is desired an aliphatic or aromatic alcohol may be added to inhibit the polymerization.

Another method to generate a proton comprises combining a Group 1 or Group 2 metal cation, preferably lithium, with water, preferably in a wet, non-protic organic solvent, in the presence of a Lewis base that does not interfere with polymerization. A wet solvent is defined to be a hydrocarbon solvent partially or fully saturated with water. It has been observed that when a Lewis base, such as isobutylene, is present with the Group 1 or 2 metal cation and the water, a proton is generated. In a preferred embodiment the non-coordinating anion is also present in the "wet" solvent such that active catalyst is generated when the Group 1 or 2 metal cation is added.


With reference to class (E), another preferred source for the cation is substituted germanium, tin or lead cations. Preferred non-limiting examples of such cations include substances having the formula:



-18-

wherein  $R^1$ ,  $R^2$  and  $R^3$ , are independently hydrogen, or a linear, branched or cyclic aromatic or aliphatic group, and M is germanium, tin or lead with the proviso that only one of  $R^1$ ,  $R^2$  and  $R^3$  may be hydrogen. Preferably, none of  $R^1$ ,  $R^2$  and  $R^3$  are H. Preferably,  $R^1$ ,  $R^2$  and  $R^3$  are, independently, a  $C_1$  to  $C_{20}$  aromatic or aliphatic group. Non-limiting examples of useful aromatic groups may be selected from the group comprising phenyl, tolyl, xylyl and biphenyl. Non-limiting examples of useful aliphatic groups may be selected from the group comprising methyl, ethyl, propyl, butyl, pentyl, hexyl, octyl, nonyl, decyl, dodecyl, 3-methylpentyl and 3,5,5-trimethylhexyl.

10 A further preferred non-coordinating anion comprises a compound selected from the group comprising:




15 wherein:

d is an integer greater than or equal to 1;

Z is selected from the group comprising:  $OR^+$ ,  $SR^+$ ,  $SeR^+$ ,  $NR_2^+$ ,  $PR_2^+$ ,  $AsR_2^+$ ,  $SbR_2^+$ ,  $F^+$ ,  $Cl^+$ ,  $Br^+$  and  $I^+$ ;

R is selected from the group comprising hydrogen,  $C_1$ - $C_{40}$  alkyl,  $C_1$ - $C_{40}$  cycloalkyl,  $C_5$ - $C_{40}$  aryl, halogen substituted derivatives thereof and heteratom substituted derivatives thereof;

$M'$  and  $M''$  may be the same or different and each has the formula



25

wherein:

M is a metal or metalloid;

$Q_1$  to  $Q_n$  are, independently, bridged or unbridged hydride radicals, dialkylamido radicals, alkoxide and aryloxy radicals, hydrocarbyl and substituted-hydrocarbyl radicals, halocarbyl and substituted-halocarbyl radicals and hydrocarbyl and halocarbyl-substituted organometalloid radicals and any

30

-19-

one, with the proviso that not more than one of  $Q_1$  to  $Q_n$  may be a halide radical; and

$n$  is an integer representing the formal valence charge of  $M$ .

Preferably,  $M$  is selected from the group comprising B, Al, Ga and In.

5 In this embodiment, the preferred non-coordinating anion is a tetra-valent boron compound. Non-limiting examples of such compounds may be selected from the group comprising tri(phenyl)boron, tri(p-tolyl)boron, tri(o-tolyl)boron, tri(pentafluorophenyl)boron, tri(o,p-dimethylphenyl)boron, tri(m,m-dimethylphenyl)boron and (p-tri-fluoromethylphenyl)boron.

10 Further details on the interaction of the reactive cation and the non-coordination anion of the preferred cationic polymerization system may be found in published International patent application WO 95/29940.

A particularly preferred type of cationic polymerization catalyst system is disclosed in United States patent 5,448,001. In some cases, it is possible to  
15 use the coinitiator (BRR'R") disclosed in the '001 patent as the sole component of the cationic polymerization system in the present process. This approach is particularly well suited for the production of isobutylene-based polymers such as isobutylene homopolymer and the like.

As described above, the present process is particularly well suited for  
20 the production of butyl rubber and other isobutylene-based polymers. Specifically, it has been discovered that such rubbers and polymers having desirable physical properties may be produced at higher temperatures than conventionally used.

Thus, the present process may be conducted at a temperature higher than  
25 about  $-80^{\circ}\text{C}$ , preferably at a temperature in the range of from about  $-80^{\circ}\text{C}$  to about  $25^{\circ}\text{C}$ , more preferably at a temperature in the range of from about  $-40^{\circ}\text{C}$  to about  $25^{\circ}\text{C}$ , even more preferably at a temperature in the range of from about  $-30^{\circ}\text{C}$  to about  $25^{\circ}\text{C}$ , even more preferably at a temperature in the range of from about  $-20^{\circ}\text{C}$  to about  $25^{\circ}\text{C}$ , most preferably at a temperature in the  
30 range of from about  $0^{\circ}\text{C}$  to about  $25^{\circ}\text{C}$ .

-20-

Embodiments of the present invention will be described with reference to the following Examples which are provided for illustrative purposes only and should not be used to limit the scope of or construe the invention.

## 5    EXAMPLES 1-4

All glassware was dried by heating at 120°C for at least 12 hours before being assembled in a nitrogen filled dry box. Nitrogen was purified by passing sequentially over heated BASF catalyst and molecular sieves. Dichloromethane was dried by refluxing over calcium hydride under nitrogen, toluene by  
10    refluxing over sodium-benzophenone under nitrogen, and both solvents were freshly distilled under nitrogen immediately prior to use.

The diene monomers (isoprene (IP) or 2,3-dimethyl-1,3-butadiene, (DMBD)) were dried over molecular sieves and then distilled. Isobutylene (IB) was purified by passing through molecular sieve and barium oxide columns, and  
15    condensed into a graduated flask immersed in liquid nitrogen. The IB was allowed to melt, the volume was noted (~3 to ~9 mL) and the IB was then refrozen by immersing in the liquid nitrogen bath. The system was evacuated to  $10^{-1}$  to  $10^{-2}$  torr, and the IB was melted and distilled at a temperature in the range of from about -10°C to about -6.5°C (the boiling point of IB being  
20    -6.4°C at one atmosphere pressure) into the glass polymerization vessel; 6 mL of solvent (toluene) was added to the condenser which was attached to the reactor; and the solution of IB was brought to the desired temperature (usually approximately  
-30°C).

25    Solutions of  $\text{Cp}^*\text{TiMe}_3$  ( $\text{Cp}^* \equiv \eta^5$ -pentamethylcyclopentadienyl; Me  $\equiv$  methyl; usually 14 mg, 0.06 mmol; recrystallized from pentane) and  $\text{B}(\text{C}_6\text{F}_5)_3$  (usually 32 mg, 0.06 mmol; sublimed), both in 1-2 mL of solvent, were added sequentially to provide an initiator to monomer ratio of approximately 1:1500.

In some Examples, an amount of diene equivalent to ~1% (mole) of the  
30    amount of IB was added to the reaction vessel prior to the addition of initiator and co-initiator.

-21-

Solutions of olefin(s) and initiator system were generally stirred as long as possible under a static vacuum and at the predetermined temperature (by "static vacuum", it is meant that the system was closed at this point and the pressure essentially was the vapour pressure of PIB at the reaction temperature).

5 Copious amounts of polymeric materials generally began to precipitate after about 2 minutes, and reactions were terminated after 10-30 min by the addition of 5-10 mL methanol. The precipitated polymeric materials were purified of inorganic residues by dissolving in pentane or hexane and passing through a short silica column. Solvents were removed under reduced pressure and the  
10 solid, white polymers were dried at 60°C-90°C for at least two days. Control reactions were also run using just Cp\*TiMe<sub>3</sub> or B(C<sub>6</sub>F<sub>5</sub>)<sub>3</sub>.

In Table 1, there is reported the use of vacuum (where vacuum was not used, polymerization was conducted under Ar(g) at atmosphereic pressure), the presence/absence of isoprene comonomer, the polymerization temperature (T),  
15 the weight average molecular weight of the polymer product (Mw) and the polydispersity index (Mw/Mn) of the polymer product.

Table 1

Example	Vacuum	Comonomer	T	Mw, x 10 <sup>4</sup>	Mw/Mn
20 1	No	No	-32°C	41.3	2.0
2	Yes	No	-32°C	61.6	2.0
3	No	Yes	-30°C	11.6	1.6
4	Yes	Yes	-30°C	14.4	1.8

25

As will be apparent to those of skill in the art, a vacuum was not applied during polymerization in Examples 1 and 3. Accordingly, Examples 1 and 3 are provided for comparative purposes only and are not encompassed by the present invention.

-22-

The results in Table 1 support the conclusion that conducting the polymerization of isobutylene at subatmospheric pressure (Example 2) results in the production of a polymer having a higher Mw when compared to conducting the polymerization of isobutylene at atmospheric pressure (Example 1). Similarly, the results in Table 1 support the conclusion that conducting the polymerization of isobutylene/isoprene at subatmospheric pressure (Example 4) results in the production of a copolymer having a higher Mw when compared to conducting the polymerization of isobutylene/isoprene at atmospheric pressure (Example 3).

10

All publications, patents and patent applications referred to herein are incorporated by reference in their entirety to the same extent as if each individual publication, patent or patent application was specifically and individually indicated to be incorporated by reference in its entirety.




What is claimed is:

1. A process for polymerizing a cationically polymerizable olefin comprising the step of polymerizing at least one cationically polymerizable olefin at a subatmospheric pressure in the presence of a cationic polymerization catalyst system.
2. The process defined in claim 1, wherein said step of polymerizing is conducted at a temperature higher than about  $-80^{\circ}\text{C}$ .
3. The process defined in claim 1, wherein said step of polymerizing is conducted at a temperature in the range of from about  $-80^{\circ}\text{C}$  to about  $25^{\circ}\text{C}$ .
4. The process defined in claim 1, wherein said step of polymerizing is conducted at a temperature in the range of from about  $-40^{\circ}\text{C}$  to about  $25^{\circ}\text{C}$ .
5. The process defined in claim 1, wherein said step of polymerizing is conducted at a temperature in the range of from about  $-30^{\circ}\text{C}$  to about  $25^{\circ}\text{C}$ .
6. The process defined in claim 1, wherein said step of polymerizing is conducted at a temperature in the range of from about  $-20^{\circ}\text{C}$  to about  $25^{\circ}\text{C}$ .
7. The process defined in claim 1, wherein said step of polymerizing is conducted at a temperature in the range of from about  $0^{\circ}\text{C}$  to about  $25^{\circ}\text{C}$ .
8. The process defined in any one of claims 1-7, wherein the subatmospheric pressure is less than about 100 kPa.
9. The process defined in any one of claims 1-7, wherein the subatmospheric pressure is less than about 90 kPa.

-24-

10. The process defined in any one of 1-7, wherein the subatmospheric pressure is in the range of from about 0.00001 to about 50 kPa.
11. The process defined in any one of claims 1-7, wherein the subatmospheric pressure is in the range of from about 0.0001 to about 40 kPa.
12. The process defined in any one of claims 1-7, wherein the subatmospheric pressure is in the range of from about 0.0001 to about 30 kPa.
13. The process defined in any one of claims 1-7, wherein the subatmospheric pressure is in the range of from about 0.0001 to about 15 kPa.
14. The process defined in any one of claims 1-13, wherein the cationic polymerization system comprises: (i) a reactive cation, and (ii) a non-coordinating anion.
15. The process defined in claim 14, wherein the reactive cation comprises a cyclopentadienyl transition metal complex.
16. The process defined in claim 15, wherein the transition metal complex comprises a compound selected from the group comprising:



-25-

wherein:

(A-Cp) is either (Cp)(Cp\*) or Cp-A'-Cp\*:

Cp and Cp\* are the same or different cyclopentadienyl rings substituted with from 0 to 5 substituent groups S, each substituent group S being, independently, a radical group selected from the group comprising hydrocarbyl, substituted-hydrocarbyl, halocarbyl, substituted-halocarbyl, hydrocarbyl-substituted organometaloid, halocarbyl-substituted organometaloid, disubstituted boron, disubstituted pnictogen, substituted chalcogen or halogen radicals, or Cp and Cp\* are cyclopentadienyl rings in which any two adjacent S groups are joined forming a C<sub>4</sub> to C<sub>20</sub> ring system to give a saturated or unsaturated polycyclic cyclopentadienyl ligand;

R is a substituent on one of the cyclopentadienyl radicals which is also bonded to the metal atom;

A' is a bridging group, which group may serve to restrict rotation of the Cp and Cp\* rings or (C<sub>5</sub>H<sub>5-y-x</sub>S<sub>x</sub>) and JR'(<sub>z-1-y</sub>) groups:

M is a Group 4,5, or 6 transition metal;

y is 0 or 1;

(C<sub>5</sub>H<sub>5-y-x</sub>S<sub>x</sub>) is a cyclopentadienyl ring substituted with from 0 to 5 S radicals;

x is from 0 to 5;

JR'(<sub>z-1-y</sub>) is a heteroatom ligand in which J is a Group 15 element with a coordination number of three or a Group 16 element with a coordination number of 2, preferably nitrogen, phosphorus, oxygen or sulfur;


R" is a hydrocarbyl group;

X and X<sup>1</sup> are independently a hydride radical, hydrocarbyl radical, substituted hydrocarbyl radical, halocarbyl radical, substituted halocarbyl radical, and hydrocarbyl- and halocarbyl-substituted organometaloid radical, substituted pnictogen radical, or substituted chalcogen radicals; and

L is an olefin, diolefin or aryne ligand, or a neutral Lewis base.

-26-

17. The process defined in claim 14, wherein the reactive cation comprises a cationic compound having the formula:



wherein  $\text{R}^1$ ,  $\text{R}^2$  and  $\text{R}^3$  are, independently, hydrogen, or a linear, branched or cyclic aromatic or aliphatic group, with the proviso that only one of  $\text{R}^1$ ,  $\text{R}^2$  and  $\text{R}^3$  may be hydrogen.


18. The process defined in claim 17, wherein none of  $\text{R}^1$ ,  $\text{R}^2$  and  $\text{R}^3$  are H.

19. The process defined in claim 17, wherein  $\text{R}^1$ ,  $\text{R}^2$  and  $\text{R}^3$  are, independently, a  $\text{C}_5$  to  $\text{C}_{20}$  aromatic or a  $\text{C}_1$  to  $\text{C}_{20}$  aliphatic group.

20. The process defined in claim 19, wherein the aromatic group is selected from the group comprising phenyl, tolyl, xylyl and biphenyl.

21. The process defined in claim 19, wherein the aliphatic group is selected from the group comprising methyl, ethyl, propyl, butyl, pentyl, hexyl, octyl, nonyl, decyl, dodecyl, 3-methylpentyl and 3,5,5-trimethylhexyl.

22. The process defined in claim 14, wherein the reactive cation comprises a cationic compound having the formula:



-27-

wherein  $R^1$ ,  $R^2$  and  $R^3$  are, independently, hydrogen, or a linear, branched or cyclic aromatic or aliphatic group, with the proviso that only one of  $R^1$ ,  $R^2$  and  $R^3$  may be hydrogen.

23. The process defined in claim 22, wherein none of  $R^1$ ,  $R^2$  and  $R^3$  are H.

24. The process defined in claim 22, wherein  $R^1$ ,  $R^2$  and  $R^3$  are, independently, a  $C_5$  to  $C_{20}$  aromatic or a  $C_1$  to  $C_{20}$  aliphatic group.


25. The process defined in claim 22, wherein  $R^1$ ,  $R^2$  and  $R^3$  are, independently, a  $C_1$  to  $C_8$  alkyl group.

26. The process defined in claim 24, wherein the aromatic group is selected from the group comprising phenyl, tolyl, xylyl and biphenyl.

27. The process defined in claim 24, wherein the aliphatic group is selected from the group comprising methyl, ethyl, propyl, butyl, pentyl, hexyl, octyl, nonyl, decyl, dodecyl, 3-methylpentyl and 3,5,5-trimethylhexyl.

28. The process defined in claim 14, wherein the reactive cation comprises a cationic compound selected from the group comprising trimethylsilylium, triethylsilylium and benzyldimethylsilylium.

29. The process defined in claim 14, wherein the reactive cation comprises a cationic compound having the formula:



-28-

wherein  $R^1$ ,  $R^2$  and  $R^3$  are, independently, hydrogen, or a linear, branched or cyclic aromatic or aliphatic group, and M is germanium, tin or lead with the proviso that only one of  $R^1$ ,  $R^2$  and  $R^3$  may be hydrogen.


30. The process defined in claim 29, wherein none of  $R^1$ ,  $R^2$  and  $R^3$  are H.

31. The process defined in claim 29, wherein  $R^1$ ,  $R^2$  and  $R^3$  are, independently, a  $C_5$  to  $C_{20}$  aromatic or a  $C_1$  to  $C_{20}$  aliphatic group.

32. The process defined in claim 31, wherein the aromatic group is selected from the group comprising phenyl, tolyl, xylyl and biphenyl.

33. The process defined in claim 31, wherein the aliphatic group is selected from the group comprising methyl, ethyl, propyl, butyl, pentyl, hexyl, octyl, nonyl, decyl, dodecyl, 3-methylpentyl and 3,5,5-trimethylhexyl.

34. The process defined in any one of claims 14-33, wherein the non-coordinating anion has the formula:



wherein:

$M'$  is a metal or metalloid;

$Q_1$  to  $Q_n$  are, independently, bridged or unbridged hydride radicals, dialkylamido radicals, alkoxide and aryloxy radicals, hydrocarbyl and substituted-hydrocarbyl radicals, halocarbyl and substituted-halocarbyl radicals and hydrocarbyl and halocarbyl-substituted organometalloid radicals and any one, with the proviso that not more than one of  $Q_1$  to  $Q_n$  may be a halide radical;

$m$  is an integer representing the formal valence charge of  $M$ ;

$n$  is the total number of ligands  $Q$ ; and

-29-

d is an integer greater than or equal to 1.

35. The process defined in claim 34, wherein the metal is selected from the group comprising aluminum, gold and platinum.

36. The process defined in claim 34, wherein the metalloid is selected from the the group comprising boron, phosphorus and silicon.

37. The process defined in claim 34, wherein

M' is boron;

n=4;

Q<sub>1</sub> and Q<sub>2</sub> are the same or different aromatic or substituted-aromatic hydrocarbon radicals containing from about 6 to about 20 carbon atoms and may be linked to each other through a stable bridging group; and

Q<sub>3</sub> and Q<sub>4</sub> are, independently, hydride radicals, hydrocarbyl and substituted-hydrocarbyl radicals, halocarbyl and substituted-halocarbyl radicals, hydrocarbyl- and halocarbyl-substituted organometalloid radicals, disubstituted pnictogen radicals, substituted chalcogen radicals and halide radicals, with the proviso that Q<sub>3</sub> and Q<sub>4</sub> are not halide at the same time.

38. The process defined in claim 37, wherein:


M' is boron;

n = 4;

Q<sub>1</sub>, Q<sub>2</sub> and Q<sub>3</sub> are each (C<sub>6</sub>F<sub>5</sub>); and

Q<sub>4</sub> is as defined above.

39. The process defined in any one of claims 14-33, wherein the non-coordinating anion comprises a compound selected from the group comprising:



-30-


wherein:

d is an integer greater than or equal to 1;

Z is selected from the group comprising:  $\text{OR}^-$ ,  $\text{SR}^-$ ,  $\text{SeR}^-$ ,  $\text{NR}_2^-$ ,  $\text{PR}_2^-$ ,  $\text{AsR}_2^-$ ,  $\text{SbR}_2^-$ ,  $\text{F}^-$ ,  $\text{Cl}^-$ ,  $\text{Br}^-$  and  $\text{I}^-$ ;

R is selected from the group comprising hydrogen,  $\text{C}_1$ - $\text{C}_{40}$  alkyl,  $\text{C}_1$ - $\text{C}_{40}$  cycloalkyl,  $\text{C}_5$ - $\text{C}_{40}$  aryl, halogen substituted derivatives thereof and heteratom substituted derivatives thereof;

M' and M" may be the same or different and each has the formula



wherein:

M is a metal or metalloid;

$\text{Q}_1$  to  $\text{Q}_n$  are, independently, bridged or unbridged hydride radicals, dialkylamido radicals, alkoxide and aryloxy radicals, hydrocarbyl and substituted-hydrocarbyl radicals, halocarbyl and substituted-halocarbyl radicals and hydrocarbyl and halocarbyl-substituted organometalloid radicals and any one, with the proviso that not more than one of  $\text{Q}_1$  to  $\text{Q}_n$  may be a halide radical; and

n is an integer representing the formal valence charge of M.

40. The process defined in claim 39, wherein M is selected from the group comprising B, Al, Ga and In.

41. The process defined in any one of claims 14-33, wherein the non-coordinating anion is a tetra-valent boron compound.

42. The process defined in claim 41, wherein the tetra-valent boron compound is selected from the group comprising tri(phenyl)boron, tri(p-tolyl)boron, tri(o-tolyl)boron, tri(pentafluorophenyl)boron, tri(o,p-



-31-

dimethylphenyl)boron, tri(m,m-dimethylphenyl)boron and (p-tri-fluoromethylphenyl)boron.

43. The process defined in any one of claims 14-33, wherein the non-coordinating anion is selected from the group comprising boranes and carboranes.

44. The process defined in any one of claims 14-33, wherein the non-coordinating anion is selected from the group comprising dodecaborate, decachlorododecaborate, dodecachlorododecaborate, 1-carbadecaborate, 1-carbaundecaborate, 1-trimethylsilyl-1-carbadecaborate.

45. The process defined in any one of claims 14-33, wherein the non-coordinating anion is selected from the group comprising decaborane(14), 7,8-dicarbadecaborane(13), 2,7-dicarbaundecaborane(13), undecahydrido-7,8-dimethyl-7,8-dicarbaundecaborane, 6-carbadecaborate(12), 7-carbaundecaborate and 7,8-dicarbaundecaborate.

46. The process defined in any one of claims 14-33, wherein the non-coordinating anion comprises a metalloborane anion selected from the group comprising bis(nonahydrido-1,3-dicarbanonaborato)cobaltate(III), bis(undecahydrido-7,8-dicarbaundecaborato)ferrate(III), bis(undecahydrido-7,8-dicarbaundecaborato)cobaltate(III), bis(undecahydrido-7,8-dicarbaborato)nikelate(III), bis(nonahydrido-7,8-dimethyl-7,8-dicarbaundecaborato)ferrate(III), bis(tribromooctahydrido-7,8-dicarbaundecaborato)cobaltate(III), bis(undecahydridodicarbadodecaborato)cobaltate(III) and bis(undecahydrido-7-carbaundecaborato)cobaltate(III).

47. The process defined in any one of claims 1-46, wherein said step of polymerizing is conducted under substantially anhydrous conditions.

48. The process defined in any one of claims 1-47, wherein said step of polymerizing is conducted in the substantial absence of a diluent.
49. The process defined in any one of claims 1-47, wherein said step of polymerizing is conducted in the presence of a diluent.
50. The process defined in claim 49, wherein the diluent is selected from the group comprising polar diluents, non-polar diluents and mixtures thereof.
51. The process defined in claim 49, wherein the diluent is selected from the group comprising haloaromatic compounds, hexane, heptane, halogenated hydrocarbons and mixtures thereof.
52. The process defined in claim 49, wherein the diluent is selected from the group comprising methyl cyclohexane, ethyl cyclohexane, propyl cyclohexane, chlorobenzene, bromobenzene, fluorobenzene, iodobenzene, methyl chloride, methylene chloride, ethyl chloride, propyl chloride, butyl chloride, chloroform and mixtures thereof.
53. The process defined in any one of claims 1-52, wherein at least one cationically polymerizable olefin is selected from the group comprising an olefin, a styrenic olefin, a heteroatom olefin and mixtures thereof.
54. The process defined in claim 53, wherein the olefin comprises a  $C_2$ - $C_{30}$  olefin.
55. The process defined in claim 53, wherein the olefin comprises a  $C_2$ - $C_{20}$  olefin.

-33-

56. The process defined in claim 53, wherein the olefin is selected from the group comprising ethylene, propylene, butene, pentene, hexene, heptene, octene, nonene, decene, dodecene, dodecyldocecene, 3-methylpentene-1, 3,5,5-trimethylhexene-1, isobutylene, 2-methyl-butene, 2-methyl-pentene, vinyl ether, vinyl carbazole and mixtures thereof.

57. The process defined in claim 53, wherein the styrenic olefin is selected from the group comprising styrene,  $C_1$ - $C_{60}$  alkyl substituted styrene and mixtures thereof.

58. The process defined in claim 53, wherein the styrenic olefin is selected from the group comprising styrene,  $\alpha$ -methyl styrene, p-chlorostyrene and p-methylstyrene and mixtures thereof.

59. The process defined in claim 53, wherein the heteroatom olefin is selected from the group comprising alkyl vinyl ethers, alkyl, amines, alkenyl amines and aryl amines.

60. The process defined in claim 53, wherein the heteroatom olefin is selected from the group comprising methyl vinyl ether, isobutylvinyl ether, butyl vinyl ether, vinyl carbazole and mixtures thereof.

61. The process defined in any one of claims 1-52, wherein the at least one cationically polymerizable olefin comprises a mixture of isobutylene and p-methyl styrene.

62. The process defined in any one of claims 1-60, wherein said step of polymerization is conducted in the presence of the at least one cationically polymerizable olefin and a diene monomer.

-34-

63. The process defined in claim 62, wherein the diene monomer is conjugated.

64. The process defined in any one of claims 1-60, wherein the at least one cationically polymerizable olefin comprises a mixture of isobutylene and isoprene.

65. The process defined in claim 62, wherein the diene monomer is unconjugated.

# INTERNATIONAL SEARCH REPORT

International Application No

PCT/CA 99/00644

A. CLASSIFICATION OF SUBJECT MATTER  
IPC 7 C08F10/10 C08F4/643

According to International Patent Classification (IPC) or to both national classification and IPC

## B. FIELDS SEARCHED

Minimum documentation searched (classification system followed by classification symbols)

IPC 7 C08F

Documentation searched other than minimum documentation to the extent that such documents are included in the fields searched

Electronic data base consulted during the international search (name of data base and, where practical, search terms used)

## C. DOCUMENTS CONSIDERED TO BE RELEVANT

Category *	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
X	WO 94 21700 A (EXXON CHEMICAL PATENTS INC) 29 September 1994 (1994-09-29)	1-16, 34, 36, 41, 49-51, 53-56
Y	examples 1,10  claims 1,5-8	1,14, 17-38, 41-46
Y	WO 95 29940 A (EXXON CHEMICAL PATENTS INC) 9 November 1995 (1995-11-09) cited in the application abstract page 5, line 33 -page 12, line 25 examples A,C,D,E	1,14, 17-38, 41-46

---  
-/--

☒ Further documents are listed in the continuation of box C.

☒ Patent family members are listed in annex.

### \* Special categories of cited documents :

- "A" document defining the general state of the art which is not considered to be of particular relevance
- "E" earlier document but published on or after the international filing date
- "L" document which may throw doubts on priority claim(s) or which is cited to establish the publication date of another citation or other special reason (as specified)
- "O" document referring to an oral disclosure, use, exhibition or other means
- "P" document published prior to the international filing date but later than the priority date claimed

- "T" later document published after the international filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention
- "X" document of particular relevance; the claimed invention cannot be considered novel or cannot be considered to involve an inventive step when the document is taken alone
- "Y" document of particular relevance; the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art.
- "8" document member of the same patent family

Date of the actual completion of the international search

1 November 1999

Date of mailing of the international search report

08/11/1999

Name and mailing address of the ISA

European Patent Office, P.B. 5818 Patentlaan 2  
NL - 2280 HV Rijswijk  
Tel. (+31-70) 340-2040, Tx. 31 651 epo nl.  
Fax: (+31-70) 340-3016

Authorized officer

Gamb, V

# INTERNATIONAL SEARCH REPORT

International Application No

PCT/CA 99/00644

## C.(Continuation) DOCUMENTS CONSIDERED TO BE RELEVANT

Category	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
X	US 5 635 573 A (HARRINGTON BRUCE A ET AL) 3 June 1997 (1997-06-03)  column 29 -column 30; example 42; table 2 claims 1,2  ---	1,2, 8-11, 14-16, 34,36, 41, 49-51, 53-56
X	EP 0 277 003 A (EXXON CHEMICAL PATENTS INC) 3 August 1988 (1988-08-03) cited in the application  example 24 claim 11  ---	1,2,8,9, 14-16, 34,44, 45, 49-51, 53-56
X	BOCHMANN M ET AL: "Cationic group IV metal alkyl complexes and their role as olefin polymerization catalysts: The formation of ethyl-bridged dinuclear and heterodinuclear zirconium and hafnium complexes" JOURNAL OF ORGANOMETALLIC CHEMISTRY, vol. 497, no. 1, 26 July 1995 (1995-07-26), page 55-59 XP004023842 ISSN: 0022-328X page 57; table 1  ---	1-7, 14-16, 34,36, 41, 49-51, 53-56
A	EP 0 277 004 A (EXXON CHEMICAL PATENTS INC) 3 August 1988 (1988-08-03) cited in the application examples 1,2  ---	1
A	US 5 066 741 A (CAMPBELL JR RICHARD E) 19 November 1991 (1991-11-19) cited in the application column 8, line 29 - line 34 claims 1-3  -----	1

# INTERNATIONAL SEARCH REPORT

Information on patent family members

International Application No

PCT/CA 99/00644

Patent document cited in search report	Publication date	Patent family member(s)	Publication date
WO 9421700 A	29-09-1994	US 5391629 A CA 2158868 A EP 0738290 A JP 9500150 T	21-02-1995 29-09-1994 23-10-1996 07-01-1997
WO 9529940 A	09-11-1995	AU 2369495 A BR 9507536 A CA 2188951 A CN 1159812 A CZ 9603149 A EP 0757698 A HU 76863 A JP 10504048 T PL 316989 A	29-11-1995 18-11-1997 09-11-1995 17-09-1997 15-07-1993 12-02-1997 29-12-1997 14-04-1998 03-03-1997
US 5635573 A	03-06-1997	NONE	
EP 0277003 A	03-08-1988	AT 146798 T AU 610863 B AU 1294588 A CA 1338687 A CA 1340136 A DE 3855727 D DK 548988 A EP 0478913 A ES 2095273 T FI 884486 A IL 85098 A JP 2880176 B JP 1501950 T PT 86671 A RU 2074770 C US 5384299 A US 5391629 A US 5408017 A WO 8805792 A US 5407884 A US 5621126 A US 5483014 A US 5470927 A US 5599761 A US 5198401 A US 5278119 A YU 16188 A YU 178789 A	15-01-1997 30-05-1991 24-08-1988 29-10-1996 17-11-1998 06-02-1997 30-11-1988 08-04-1992 16-02-1997 29-09-1988 29-03-1992 05-04-1999 06-07-1989 30-01-1989 10-03-1997 24-01-1995 21-02-1995 18-04-1995 11-08-1988 18-04-1995 15-04-1997 09-01-1996 28-11-1995 04-02-1997 30-03-1993 11-01-1994 28-02-1990 30-04-1991
EP 0277004 A	03-08-1988	AT 145218 T AT 145211 T AU 617990 B AU 1245288 A CA 1339142 A CA 1337142 A CZ 8800579 A DE 3855666 D DE 3855668 D DK 548888 A EP 0468537 A EP 0561479 A	15-11-1996 15-11-1996 12-12-1991 24-08-1988 29-07-1997 26-09-1995 15-02-1995 19-12-1996 19-12-1996 30-11-1988 29-01-1992 22-09-1993

# INTERNATIONAL SEARCH REPORT

Information on patent family members

International Application No

PCT/CA 99/00644

Patent document cited in search report	Publication date	Patent family member(s)	Publication date
EP 0277004 A		EP 0558158 A	01-09-1993
		EP 0949278 A	13-10-1999
		EP 0949279 A	13-10-1999
		ES 2094174 T	16-01-1997
		ES 2094461 T	16-01-1997
		FI 884487 A	29-09-1988
		HU 211065 B	30-10-1995
		IL 85097 A	16-02-1992
		JP 2918193 B	12-07-1999
		JP 8034809 A	06-02-1996
		JP 8034810 A	06-02-1996
		JP 1502036 T	13-07-1989
		KR 9615192 B	01-11-1996
		NO 179589 B	29-07-1996
		PT 86672 A	30-01-1989
		RU 2062649 C	27-06-1996
		US 5384299 A	24-01-1995
		US 5391629 A	21-02-1995
		US 5408017 A	18-04-1995
		WO 8805793 A	11-08-1988
		US 5621126 A	15-04-1997
		US 5470927 A	28-11-1995
		US 5599761 A	04-02-1997
		US 5153157 A	06-10-1992
		US 5198401 A	30-03-1993
		US 5241025 A	31-08-1993
		YU 16288 A	28-02-1990
		YU 178689 A	30-04-1991
US 5066741 A	19-11-1991	AT 140242 T	15-07-1996
		AU 635967 B	08-04-1993
		AU 6327990 A	11-04-1991
		CA 2024830 A	30-03-1991
		CN 1050546 A, B	10-04-1991
		DE 69027729 D	14-08-1996
		DE 69027729 T	23-01-1997
		EP 0421659 A	10-04-1991
		ES 2088981 T	01-10-1996
		JP 2942337 B	30-08-1999
		JP 3124706 A	28-05-1991
		SG 52564 A	28-09-1998
		RU 2011654 C	30-04-1994



**This Page is Inserted by IFW Indexing and Scanning  
Operations and is not part of the Official Record**

**BEST AVAILABLE IMAGES**

Defective images within this document are accurate representations of the original documents submitted by the applicant.

Defects in the images include but are not limited to the items checked:

☐ **BLACK BORDERS**

☐ **IMAGE CUT OFF AT TOP, BOTTOM OR SIDES**

☐ **FADED TEXT OR DRAWING**

☐ **BLURRED OR ILLEGIBLE TEXT OR DRAWING**

☐ **SKEWED/SLANTED IMAGES**

☐ **COLOR OR BLACK AND WHITE PHOTOGRAPHS**

☐ **GRAY SCALE DOCUMENTS**

☐ **LINES OR MARKS ON ORIGINAL DOCUMENT**

☐ **REFERENCE(S) OR EXHIBIT(S) SUBMITTED ARE POOR QUALITY**

☐ **OTHER:** \_\_\_\_\_

**IMAGES ARE BEST AVAILABLE COPY.**

**As rescanning these documents will not correct the image problems checked, please do not report these problems to the IFW Image Problem Mailbox.**

**THIS PAGE BLANK (USPTO)**